



De	Di	t	t'	ho	ho'	lo
31.50	16.30	0.80		1.05		1.85

S/ho	S	F	I	II	III	IV	OM
0.10	0.11	178.36	-322	-17	188	30	-108
0.20	0.21	323.16	-626	-16	364	49	-215
0.25	0.26	384.15	-771	-9	448	54	-269
0.30	0.32	438.15	-912	3	529	56	-323
0.40	0.42	527.05	-1180	39	683	52	-431
0.50	0.53	593.58	-1430	94	825	36	-538
0.60	0.63	641.48	-1663	166	955	9	-646
0.70	0.74	674.47	-1878	256	1074	-30	-754
0.75	0.79	686.54	-1978	308	1130	-53	-808
0.80	0.84	696.27	-2075	364	1182	-80	-861
0.90	0.95	710.62	-2254	489	1278	-142	-969
1.00	1.05	721.25	-2415	633	1363	-215	-1077


Group 1 F(0.75 ho) 686.54 N



De	Di	t	t'	ho	ho'	lo
31.50	16.30	1.25		0.90		2.15

S/ho	S	F	I	II	III	IV	OM
0.10	0.09	340.36	-328	80	186	-25	-144
0.20	0.18	647.70	-644	173	363	-59	-288
0.25	0.23	790.14	-797	224	449	-80	-361
0.30	0.27	925.71	-946	278	532	-102	-433
0.40	0.36	1178.04	-1235	397	692	-153	-577
0.50	0.45	1408.37	-1512	530	844	-212	-721
0.60	0.54	1620.36	-1775	675	988	-279	-865
0.70	0.63	1817.68	-2025	833	1123	-356	-1009
0.75	0.68	1911.98	-2145	917	1187	-397	-1082
0.80	0.72	2004.00	-2261	1004	1250	-440	-1154
0.90	0.81	2182.98	-2485	1189	1368	-533	-1298
1.00	0.90	2358.29	-2696	1386	1478	-634	-1442

Group 2 F(0.75 ho) 1911.98 N







De	Di	t	t'	ho	ho'	lo
31.50	16.30	1.50		0.90		2.40

S/ho	S	F	I	II	III	IV	OM
0.10	0.09	532.94	-369	121	207	-47	-173
0.20	0.18	1026.28	-726	254	405	-102	-346
0.25	0.23	1259.47	-899	326	501	-132	-433
0.30	0.27	1484.40	-1069	401	595	-165	-519
0.40	0.36	1911.72	-1399	561	777	-237	-692
0.50	0.45	2312.63	-1716	734	950	-317	-865
0.60	0.54	2691.54	-2019	920	1115	-406	-1038
0.70	0.63	3052.84	-2310	1119	1271	-503	-1211
0.75	0.68	3228.26	-2451	1223	1346	-555	-1298
0.80	0.72	3400.94	-2588	1331	1419	-609	-1384
0.90	0.81	3740.23	-2852	1556	1558	-723	-1557
1.00	0.90	4075.12	-3104	1795	1689	-846	-1730


Group 2 F(0.75 ho) 3228.26 N



De	Di	t	t'	ho	ho'	lo
31.50	16.30	1.75		0.70		2.45

S/ho	S	F	I	II	III	IV	OM
0.10	0.07	572.16	-297	147	163	-67	-157
0.20	0.14	1122.59	-587	302	322	-138	-314
0.25	0.18	1390.40	-729	382	399	-176	-393
0.30	0.21	1653.68	-869	465	475	-215	-471
0.40	0.28	2167.86	-1142	636	623	-297	-628
0.50	0.35	2667.55	-1408	814	766	-384	-785
0.60	0.42	3155.16	-1666	1001	904	-476	-942
0.70	0.49	3633.10	-1916	1195	1037	-573	-1099
0.75	0.53	3869.21	-2038	1296	1102	-623	-1178
0.80	0.56	4103.80	-2158	1398	1165	-675	-1256
0.90	0.63	4569.67	-2392	1608	1288	-783	-1413
1.00	0.70	5033.11	-2619	1826	1405	-895	-1570

Group 2 F(0.75 ho) 3869.21 N







De	Di	t	t'	ho	ho'	lo
31.50	16.30	2.00		0.75		2.75

S/ho	S	F	I	II	III	IV	OM
0.10	0.08	901.75	-359	186	196	-85	-192
0.20	0.15	1772.93	-708	381	387	-176	-385
0.25	0.19	2198.12	-879	481	480	-224	-481
0.30	0.23	2616.95	-1048	585	572	-273	-577
0.40	0.30	3437.19	-1380	798	751	-376	-769
0.50	0.38	4237.06	-1702	1020	924	-484	-961
0.60	0.45	5019.95	-2015	1251	1091	-599	-1154
0.70	0.53	5789.26	-2319	1491	1252	-719	-1346
0.75	0.56	6169.88	-2467	1615	1331	-782	-1442
0.80	0.60	6548.37	-2614	1741	1408	-845	-1538
0.90	0.68	7300.70	-2899	1999	1557	-978	-1730
1.00	0.75	8049.63	-3176	2267	1701	-1115	-1923

Group	2	F(0.75 ho)	6169.88	N
-------	---	------------	---------	---




Fatigue Life
 a : 2,000,000 Cycle
 b : 500,000 Cycle
 c : 100,000 Cycle



De	Di	t	t'	ho	ho'	lo
34.00	12.20	1.00		1.25		2.25

S/ho	S	F	I	II	III	IV	OM
0.10	0.13	293.31	-416	2	179	29	-120
0.20	0.25	533.65	-810	27	347	47	-240
0.25	0.31	635.80	-999	47	427	52	-300
0.30	0.38	726.91	-1182	73	505	54	-360
0.40	0.50	878.96	-1533	140	651	50	-480
0.50	0.63	995.70	-1862	230	786	36	-600
0.60	0.75	1083.00	-2169	341	910	10	-720
0.70	0.88	1146.77	-2454	474	1024	-27	-840
0.75	0.94	1171.66	-2588	549	1076	-49	-900
0.80	1.00	1192.87	-2717	629	1126	-74	-960
0.90	1.13	1227.21	-2959	806	1218	-133	-1080
1.00	1.25	1255.66	-3179	1004	1298	-203	-1200

Group	1	F(0.75 ho)	1171.66	N
-------	---	------------	---------	---



Fatigue Life
 a : 2,000,000 Cycle
 b : 500,000 Cycle
 c : 100,000 Cycle