



De	Di	t	t'	ho	ho'	lo
34.00	16.30	1.75		0.90		2.65

S/ho	S	F	1	II	III	IV	OM
0.10	0.09	651.83	-350	140	182	-53	-166
0.20	0.18	1265.70	-689	291	357	-113	-332
0.25	0.23	1559.72	-855	370	442	-145	-415
0.30	0.27	1845.83	-1017	453	525	-180	-498
0.40	0.36	2396.42	-1334	626	686	-253	-663
0.50	0.45	2921.71	-1640	810	841	-333	-829
0.60	0.54	3425.91	-1935	1005	989	-420	-995
0.70	0.63	3913.23	-2218	1211	1130	-514	-1161
0.75	0.68	4151.89	-2356	1318	1198	-563	-1244
0.80	0.72	4387.90	-2491	1428	1265	-614	-1327
0.90	0.81	4854.13	-2753	1657	1392	-722	-1493
1.00	0.90	5316.15	-3003	1896	1513	-836	-1658


Group 2 F(0.75 ho) 4151.89 N



De	Di	t	t'	ho	ho'	lo
34.00	16.30	2.00		0.85		2.85

S/ho	S	F	1	II	III	IV	OM
0.10	0.09	865.20	-358	171	184	-69	-179
0.20	0.17	1693.86	-707	351	362	-145	-358
0.25	0.21	2095.75	-877	445	449	-185	-448
0.30	0.26	2490.02	-1045	541	534	-226	-537
0.40	0.34	3257.76	-1374	742	700	-314	-716
0.50	0.43	4001.13	-1692	952	860	-407	-895
0.60	0.51	4724.19	-2001	1172	1014	-507	-1074
0.70	0.60	5431.01	-2300	1402	1162	-612	-1253
0.75	0.64	5779.60	-2446	1520	1234	-667	-1343
0.80	0.68	6125.65	-2589	1641	1304	-724	-1432
0.90	0.77	6812.16	-2868	1891	1440	-842	-1611
1.00	0.85	7494.62	-3138	2150	1570	-966	-1790

Group 2 F(0.75 ho) 5779.60 N







De	Di	t	t'	ho	ho'	lo
35.50	18.30	0.90		1.15		2.05

S/ho	S	F	I	II	III	IV	OM
0.10	0.12	211.66	-308	-12	179	26	-104
0.20	0.23	384.37	-598	-7	347	42	-208
0.25	0.29	457.47	-737	2	427	46	-260
0.30	0.35	522.47	-872	15	504	47	-313
0.40	0.46	630.28	-1129	53	650	41	-417
0.50	0.58	712.12	-1370	108	786	24	-521
0.60	0.69	772.34	-1593	181	911	-3	-625
0.70	0.81	815.24	-1800	270	1025	-42	-729
0.75	0.86	831.56	-1897	320	1078	-65	-781
0.80	0.92	845.17	-1989	375	1128	-91	-834
0.90	1.04	866.44	-2162	498	1220	-151	-938
1.00	1.15	883.38	-2319	637	1302	-222	-1042

Group 1 F(0.75 ho) 831.56 N




**Fatigue Life**  
 a : 2,000,000 Cycle  
 b : 500,000 Cycle  
 c : 100,000 Cycle



De	Di	t	t'	ho	ho'	lo
35.50	18.30	1.25		1.00		2.25

S/ho	S	F	I	II	III	IV	OM
0.10	0.10	318.42	-299	58	170	-14	-126
0.20	0.20	601.28	-586	128	331	-37	-252
0.25	0.25	730.60	-724	168	409	-51	-315
0.30	0.30	852.52	-860	211	484	-68	-378
0.40	0.40	1076.11	-1121	307	629	-107	-503
0.50	0.50	1275.98	-1369	416	766	-154	-629
0.60	0.60	1456.10	-1605	537	895	-209	-755
0.70	0.70	1620.41	-1828	671	1016	-272	-881
0.75	0.75	1697.88	-1935	743	1073	-307	-944
0.80	0.80	1772.87	-2038	818	1128	-344	-1007
0.90	0.90	1917.43	-2236	977	1232	-424	-1133
1.00	1.00	2058.04	-2421	1149	1329	-512	-1258

Group 2 F(0.75 ho) 1697.88 N





**Fatigue Life**  
 a : 2,000,000 Cycle  
 b : 500,000 Cycle  
 c : 100,000 Cycle



De	Di	t	t'	ho	ho'	lo
35.50	18.30	2.00		0.80		2.80

S/ho	S	F	I	II	III	IV	OM
0.10	0.08	766.63	-306	151	167	-68	-161
0.20	0.16	1504.13	-603	310	330	-141	-322
0.25	0.20	1862.97	-749	393	409	-180	-403
0.30	0.24	2215.73	-893	478	487	-220	-483
0.40	0.32	2904.68	-1174	654	638	-304	-644
0.50	0.40	3574.20	-1448	837	785	-393	-805
0.60	0.48	4227.53	-1713	1029	926	-487	-966
0.70	0.56	4867.92	-1970	1229	1062	-587	-1128
0.75	0.60	5184.27	-2095	1332	1128	-638	-1208
0.80	0.64	5498.60	-2218	1437	1193	-691	-1289
0.90	0.72	6122.80	-2459	1653	1319	-801	-1450
1.00	0.80	6743.77	-2692	1878	1439	-916	-1611

Group 2 F(0.75 ho) 5184.27 N



De	Di	t	t'	ho	ho'	lo
40.00	14.30	1.25		1.40		2.65

S/ho	S	F	I	II	III	IV	OM
0.10	0.14	411.03	-399	24	170	18	-121
0.20	0.28	754.89	-779	69	330	27	-243
0.25	0.35	903.96	-961	98	406	27	-303
0.30	0.42	1039.04	-1139	132	480	26	-364
0.40	0.56	1270.95	-1479	216	620	14	-485
0.50	0.70	1458.08	-1799	319	750	-7	-606
0.60	0.84	1607.89	-2100	443	871	-38	-728
0.70	0.98	1727.85	-2381	585	981	-79	-849
0.75	1.05	1778.97	-2514	664	1033	-103	-910
0.80	1.12	1825.42	-2642	748	1082	-130	-970
0.90	1.26	1908.06	-2884	930	1172	-191	-1091
1.00	1.40	1983.24	-3105	1132	1253	-262	-1213

Group 2 F(0.75 ho) 1778.97 N

